



**PERFORMANCE
LUBRICANTS**

Typical Dropping Points

Calcium	160F – 210F
Calcium Complex	475F – 550F
Lithium	350F – 375F
Lithium Complex	475F – 550F
Polyurea	500F – 575F
Calcium Sulfonate	500F – 550F
Aluminum	160F – 210F
Aluminum Complex	475F – 550F

ISO 9001:2008 Certified